



Adhesivos y Selladores

COLLAK, S.A. – C/. França, 3 – Pol. Ind. Pla de Llerona – 08520 Les Franqueses del Vallès – NIF A08344897
Tel.: (+34) 93 849 44 33 – Fax: (+34) 93 849 22 77 – E-mail: collak@collak.com – www.collak.com

07/21-URE-290-v1.0

URE 290

ADHESIVE FOR PVC AND RUBBER FLOORINGS

1. DESCRIPTION

Bicomponent and solvent free polyurethane adhesive. Fast setting with high final bond strength. For indoor and outdoor use. Low VOC emission.

2. APPLICATION

Adhesive suitable for bonding a wide range of materials over different substrates: porexpan, linoleum, carpets, aluminium, iron, concrete, etc. **Specially useful for bonding PVC and rubber floorings.**

PROPERTIES		
	Part A	Part B
Colour	Grey	Brown
Viscosity (Brook. HBT Sp. 6, 50 rpm) (20 °C)	90000-110000 cps	-
Mixing ratio A:B (parts by weight)	6 parts	1 part
Pot life 20° C	30 - 45 minutes.	
Performance	Notch B1	400 - 500 g/m ²
	Notch B3	700-/800 g/m ²

3. INSTRUCTIONS FOR USE

The surfaces to be bonded must be clean, dry and free of dust, grease or parting compound. Carefully mix the resin and hardener according to the proper mixing ratio and use a hand drill with stirring attachment for at least 2 minutes or until you get an homogenous paste. Then apply the product to the subfloor using a notched trowel. Install the floor covering immediately into the wet adhesive ensuring full adhesive transfer. Follow supplier recommendations of the covering material. In structural unions aluminium/aluminium it is necessary to sand the surfaces and make a proper degreased of the union area.

Fresh adhesive can be cleaned with Collak D.L. Once the product is cured tools only can be cleaned using mechanical methods.

4. PACKING

Plastic buckets of 10,5 Kg (9 Kg of part A and 1,5 Kg of component B)

5. STORAGE

In dry and cool places, at temperatures between +5 and +35 °C, the shelf life is at least 12 months from production date.

6. CAUTIONS

During the curing process, avoid the contact with the mucous (eyes, mouth, etc.) and wash the hands after use. Once cured this adhesive becomes a non hazardous product. Keep away from children. Component B contains aromatic isocyanates, for further advice read material safety data sheet available upon request.

Every endeavour has been made to ensure that the information given herein is true and reliable, but is given only for the guidance of our customers. Collak, S.A. cannot accept any responsibility for loss or damage or infringements of patent rights that may result from the use of the information, due the possibility of variations of processing or working conditions are outside our control. Users are advised to confirm the suitability of the products with their own tests. Our technical service is at customer's disposal for any conference, explanation or advise.